

PRODUCT SPECIFICATION

SAFETYWARE Chem-Pro™ Medium Duty Flocklined Nitrile Gloves

- Made from specially formulated Acrylonitrile Butadiene compound that provides outstanding protection against a wide range of chemicals including strong detergents, greases, oils, most solvents and acids.
- Offers superior resistance to abrasion, cut and puncture compared with natural rubber gloves.
- Higher durability and longer wear than natural rubber gloves.
- Does not contain latex protein.
- The patterned palm and fingers give excellent grip in both wet and dry conditions.
- Cotton flocklined offers added comfort and better absorption of perspiration.

CARE INSTRUCTION

- Carefully inspect the gloves before you put them on. Look for cracks, tears, holes, swelling or other damage. Chemicals can pass through even the smallest pinhole. If you spot any damage, discard the gloves.
- Wash the outside of your gloves with soap and water before you remove them. Always wash them when you take a break and when you are done for the day. Then thoroughly wash your hands.
- Put your gloves in proper container when you are finished with your task for the day.

APPLICATIONS

- Chemical Handling
- Oil Refining
- Agriculture
- Food Processing
- Printing Industry
- Automotive Industry

TECHNICAL DATA

| | | | |
|---------------------|---|--------------|----------|
| MATERIAL | Nitrile | COLOR | Green |
| TYPE | Cotton Flocklined | CUFF | Straight |
| CONSTRUCTION | Unsupported Gloves | | |
| THICKNESS | About 0.38 mm (15 mil) | | |
| LENGTH | About 330 mm (13 inch) | | |
| STANDARD | CE, FDA | | |
| PACKAGING | 1 pair/ polybag, 12 pairs/ bag, 144 pairs/ carton | | |

Item Code: GNF1513



ITEM CODE

| ITEM CODE | SIZE |
|---------------|------|
| GNF15130GRNSM | S |
| GNF15130GRNMD | M |
| GNF15130GRNLG | L |
| GNF15130GRNXL | XL |
| GNF15130GRN2X | 2XL |

PERFORMANCE PROPERTIES

| EN388 | | | EN374-1 | | |
|--------------------------------------|---|---|------------------------|---|--|
| ABRASION | 4 | J | N - Heptane | 6 | |
| CUT | 0 | K | Sodium Hydroxide 40% | 6 | |
| TEAR | 0 | L | Sulfuric Acid 96% | 2 | |
| PUNCTURE | 1 | N | Acetic Acid 99% | 5 | |
| CUT RESISTANCE METHOD (EN ISO 13997) | X | O | Ammonium Hydroxide 25% | 3 | |
| | | T | Formaldehyde 37% | 6 | |

